

Over 45 Years in Business

'Ask Dr Gel' • 18 Years in Boating on the Hudson

# Ask Dr. Gel

by Dave Weakley

Dave Weakley is the owner of American Boat Restoration and has been keeping boaters afloat in fine trim and good repair for over 45 years.



"Email me or call me with your questions! I'll be happy to help you out"

americanboatrestoration.com / email: boatrepair@aol.com

Office: 413.665.7424 / Cell: 518.577.7799

## Here comes the sun...

## ...and the sunscreen, hat, compound, sealer glaze & wax!

### My Tips for a healthy boat during the "dog days" of summer!

- **Establish a year round care and maintenance plan.** Your boat's gel coat is exposed to all sorts of environmental elements such as rain, salt, dirt, dust and exhaust on a daily basis. Washing with soap designed specifically for gelcoat and painted boats will help prevent the breakdown of the finish, protective wax and sealer glaze thus reducing shine and overall appearance. Don't ever use strong cleaners such as Mr. Clean, Fantastic, etc. Even dish soap is not recommended. Use Only boat soap.

- **Keep your boat clean and wax it often with UV protecting wax.** Waxing 2-3 times during the boating season is suggested. Additionally at least once a month wash/ pressure wash any trapped dirt and debris around deck, hardware and rub rails.

- **Use the correct buffing equipment and RPM speed when compounding and polishing.** You can actually burn gelcoat if the speed is too high and there is too much pressure. I recommend 600 RPM for compound and 1500 RPM for sealer glaze and wax.

I use a Dewalt variable speed on the trigger and RPM handle setting. I use good double sided "Buff & Shine" pads; heavy cut for compounding and light cut for polishing.

- **Keep your boat covered if possible** - the more canvas cover on it will result in less chalking caused by the sun.

- **If it's been hot and humid** for a long period of time and you have not used your boat open it up/ take off all the canvas cover(s) and air it out. Check for mildew and clean immediately.

- **Keep it on a trailer or a boat lift if possible.** If that is not possible and it's left in the water all season protect the hull with epoxy barrier.

- **Ventilate!** Always a good idea! This will help prevent explosions.

- **Dry out** all those wet life vests, cushions, wet dock and anchor lines, soggy beach towels, wipe down towels, ski ropes and equipment. If you have a storage/ski locker keep it dry!

- **Wipe the boat down often,** doing this will also show if there are any cosmetic damages that need to be addressed. The sooner the repairs are made the better especially if there are hair line cracks, air voids, osmotic blistering, etc.

- **Empty live well before storing**

- **Check engine mounts** to be sure all is secure and tight.

- **Check the cleats,** bow eyes, rub rail, windshields, railings, etc and make sure the sealants are good and the fasteners are tight. Check dock hardware to be sure everything is all secure. Summer storms and wind can do much damage to an unsecured boat!

- **Take it out of the water** if there will be an extended period of time that you will not be using it.

Keeping your boat in good condition by following my tips will certainly extend the life of your boat and it will hold its value longer!

### Some questions from our readers:

**"Dr Gel, Can you offer some advice on how to compound and wax my boat? What materials should I use?"** Ryan

"If you are going to compound and wax your boat you need the right materials and equipment"



Dr Gel enjoying a hot summer day.

Here's what you need; a good particle mast; compounds dry out your sinus and skin, eye protection and light weight gloves, micro fiber rags, a variable speed buffer, not an orbital buffer! Orbital buffer is good for polishing but not for compounding because you won't get the heat from it necessary to get a shine. Be sure to get a buffing pad; different from polishing pads. Use a good quality wool pad, I use a doubled sided pad. The pads are pricey, but you get what you pay for. Don't bother using a foam buffing pad as they build up static electricity and will not produce a good shine.

"As a general rule; buffing without a little heat you're not going to get the shine"

Start with using a product I have found to be excellent called Presta Supercut, course compound. Apply to the boat using a micro fiber rag. Put enough on to keep it moist; too much will sling all over and make a mess. All buffers spin clockwise so put compound on the boat and work right to left in small areas so the compound stays moist and it will avoid loading up your buffing pad. Be careful buffing around registration numbers, vinyl graphics and stripping tapes!

After using Presta Super Cut wipe the residue off



the boat. Clean the pad with a tool called a spur. I do not recommend the side of a screw driver as it tends to pull the buffing pad apart and turns the pad black. Repeat the process using Mirka 35 compound to get rid of swirl marks and minor scratches caused by the coarse compound. Again wipe off the residue and clean the pad. Next apply the TR-301 Sealer Glaze. It can be applied and removed by hand but for best results use the buffer. Wipe the boat down one last time and apply a good marine UV protecting wax. Wax is essential because the Sealer Glaze does not have UV protecting properties.

If the gelcoat has become badly chalked and it comes off onto your hands and clothes when you rub against it wet sanding and compounding will be required to bring the shine back.

Here is the basic wet sanding process;

I test spot an area starting with a professional grade gelcoat compound. If that does not remove the fade then I will wet sand using a sanding block starting with 1000 gt. During the process the sandpaper is completely saturated with water. I work 1 sq. ft at a time all the way around the boat being very consistent on how much sanding is done. The gelcoat must be sanded evenly otherwise the boat will look like a leopard. Depending on finish desired 1500 and 2000 gt is used. Final applications are professional grades of compound mentioned above, sealer glaze and UV protecting wax.

**"Hello Doctor Gel, I purchased a new boat last summer and had it winterized and bottom cleaned. I was told an acid wash was used on it. Do I need to do anything to the hull before I put it in the water"**

*Dan S.*

As mentioned in many of my previous articles; A new boat comes from the factory with sealer glaze on the gelcoat. If the hull is acid washed the protection has been removed. Gelcoat is porous and you need to re-apply sealer glaze. This also helps to prevent but will not eliminate the possible development of osmotic blisters. The best way to protect the hull and avoid having to apply sealer glaze every year after acid washing is to apply epoxy barrier paint from the water line down. You can acid wash the epoxy barrier every year. Epoxy barrier paint is the best protection against osmotic blistering. It is impervious to water where as polyester gelcoat is not. I have seen osmotic blisters on brand new boats that were in the water just one season.

\*Email us - boatrepair@aol.com other questions and/or product purchasing info.

"Once the gelcoat is refurbished back to a nice shine it is very important to keep it waxed!"  
"Waxing today will keep the Doctor away!"

### Eliminating unwanted holes:

**"Dr. Gel, I really enjoy reading your articles in Boating on The Hudson and Beyond. Thank you for sharing your knowledge. I have a question for you. I have several sea cocks that I am removing and I need to "plug" the holes. Some background, 1978 Grand Banks 36 classic, 1' and 1.5' holes, the hull goes from a about 1 1/8" thick to 3/4" solid glass! (I was very pleased to see that!). I have read several versions of filling these holes and I need to do this right. I have the tools and have done epoxy and glass mat work before.**

**If you could provide some guidance, it would be greatly appreciated."**

*J. J. FSO-MT*

*U. S. Coast Guard Auxiliary*

The fiberglass repair has to be as strong as the rest of the hull. Begin with assembling the proper safety and repair equipment.

Good quality respirator, Safety glasses, Tyvek suit, Nitrile gloves, Air compressor, Air hose, Small 90° Angle grinder to hold 1 1/2" 36 grit grinding discs, a good shop vacuum, Rags, Acetone, Razor knife, Fiberglass matting, Epoxy or Vinyl Ester resin, Hardener, Mixing cups, 2" Chip brushes, 3/4" Masking tape, Cardboard, Wax paper & Stir stick and Plastic spreader.

Don't attempt the repair with a big grinder; it's important to keep the repair area small and be surgical. This will help to keep dust down to a minimum; especially helpful if you are working inside the boat. A tyvek suit will protect your skin so you won't have fiberglass particles feeling like tiny arrows sticking in your skin.

Repairing holes has to be done correctly otherwise there will be a risk of taking on water.

Through the years I have had to repair previous repairs that failed. Most were "plug" repairs and not tapered.

When a boat is first manufactured all the resin and fiberglass chop/layers cure as a single component. It is at its strongest state. Once a hull has been damaged all repairs become secondary bonds so it is important to use the proper resin type for a strong repair that will withstand time. Never use a weaker resin than what the boat was built with. I recommend using epoxy resin to repair the Grand Banks which was built using polyester resins. Epoxy resin adheres

to polyester better than polyester adheres to itself. But! You cannot use epoxy resins if you intend to apply new gelcoat. You must use vinyl ester resins for the repair.

If you can access the inside of the boat to do the repair it will be a stronger repair and gravity will be in your favor during the process.

- Start the repair by grinding out the inside (if accessible) of the hole at a nice taper using the vacuum held close to the grinder recouping the dust. Grind all the way around the hole for a minimum diameter of four times the thickness of the hull. The more gradual the taper the better the strength of the repair and bond will be.

- Cut out round pieces cut out pieces of biaxial mat a little larger than the size of the hole. Cut another piece 1/2" larger than the first and repeat attempting to replicate the thickness of the original laminate. Lay the cut pieces one on top of each other ending with the first, smallest piece on top.

- Go under the boat and tape a piece of wax paper larger than the size of the hole over the hole.

- Cover a piece of cardboard much larger than your largest piece of fiberglass mat and cover one side with wax paper using tape to secure the wax paper tightly. Mix the epoxy resin and hardener; Next using a 2" chip brush immediately proceed to wet out your smallest piece of fiberglass cloth on the wax paper sided cardboard with resin. After applying use a plastic squeegee lightly run the edge of the squeegee across to remove the excess resin. Amount to mix will depend on size of hole.

- Go inside the boat
- Brush an even coat of activated resin around the inside of the tapered hole; apply enough to be tacky and be careful not to use an excessive amount.

- Carefully lift the first wetted piece of fiberglass cloth and lay on the hole leveling out using a chip brush; check for air bubbles and flatten out gently if needed. Air bubbles will weaken the repair.

- Repeat procedure; it is not necessary to add additional resin to the previous layer applied.

- It's not necessary to use an excessive amount of resin; the strength of the repair is in the mat. Too much resin will create a large amount of heat and may crack.

- Let set over night



### The Dog Days are coming!

- Get your grinder back out and grind flat again using the vacuum assist. As you grind you will see nice rings like you see on a cut tree stump.
- On the outside of the boat pull the wax paper off.
- It is likely you will need to apply a couple of layers of fiberglass cloth or mat and epoxy resin on the outside of the hull.
- To do this, begin with grinding a slight "belly like" indentation into the repair. Then apply the cloth and resin as you did inside.
- Let set over night; Grind flat
- Finish with barrier coat or gelcoat.

This method of repair can be used to repair tears, punctures, crushed fiberglass and delaminating areas.

*Jeff has had some experience in fiberglass work which is helpful. I am confident he can do a good repair following these procedures.*